


Rockwool 201

Lambda λ : 0,037 W/mK

Isolatiewaarde Rockwool 201



Dikte product	R-waarde	U-waarde
30 mm	0,811	1,233
35 mm	0,946	1,057
40 mm	1,081	0,925
45 mm	1,216	0,822
50 mm	1,351	0,740
55 mm	1,486	0,673
60 mm	1,622	0,617
65 mm	1,757	0,569
70 mm	1,892	0,529
75 mm	2,027	0,493
80 mm	2,162	0,463
85 mm	2,297	0,435
90 mm	2,432	0,411
95 mm	2,568	0,389
100 mm	2,703	0,370
105 mm	2,838	0,352
110 mm	2,973	0,336
115 mm	3,108	0,322
120 mm	3,243	0,308
125 mm	3,378	0,296
130 mm	3,514	0,285
135 mm	3,649	0,274
140 mm	3,784	0,264
145 mm	3,919	0,255
150 mm	4,054	0,247
155 mm	4,189	0,239
160 mm	4,324	0,231
165 mm	4,459	0,224
170 mm	4,595	0,218
175 mm	4,730	0,211
180 mm	4,865	0,206
185 mm	5,000	0,200
190 mm	5,135	0,195
195 mm	5,270	0,190
200 mm	5,405	0,185